

Star L

Star L PPS 30Y D51F

DESCRIPTION Star L PPS 30Y D51F is a PTFE Lubricated PPS Reinforced with Carbon Fiber, Injection Molding Grade. EXPERIMENTAL.

PROPERTY (1)	UNIT	STANDARD	TYPICAL VALUE (1) Dry As Moulded
PHYSICAL			
Density	g/cm ³	ASTM D 792	1.53
Mold Shrinkage, flow (4mm thickness)	%	E2P Method	0.1 - 0.3
MECHANICAL			
Flexural Modulus	MPa	ISO 178	20000
Flexural Stress	MPa	ISO 178	197
Tensile Strain, break	%	ASTM D 638	0.5
Tensile Stress, yield	MPa	ISO 527	103
IMPACT			
Izod Impact, notched 80*10*4 +23°C	kJ/m ²	ISO 180/1A	3,9
Izod Impact, unnotched 80*10*4 +23°C	kJ/m ²	ISO 180/1U	22
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	°C	ISO 75/Af	246
Melting Point DSC	°C	ISO 3146	283

CRLab 1331671 LR4111

(1) Typical values for natural color unless specified otherwise. Do not constitute a specification. Significant variations are possible for colors

Starflam, Staramide and Starpylen are registered trademarks of EUROSTAR Engineering Plastics

All information, recommendation or advice given by Eurostar Engineering Plastics Company, or any of its subsidiaries, affiliates or authorized representatives, is given in good faith. Eurostar Engineering Plastics makes no warranty or guarantee, express or implied about the information provided. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of Eurostar Engineering Plastics, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. Eurostar Engineering Plastics cannot be held responsible respectively liable for any loss incurred through the use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of Eurostar Engineering Plastics or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

Star L

Star L PPS 30Y D51F

DESCRIPTION Star L PPS 30Y D51F is a PTFE Lubricated PPS Reinforced with Carbon Fiber, Injection Molding Grade. EXPERIMENTAL.

PARAMETER	Setting	Unit
Mold Temperature	135 - 165	°C
Barrel - Zone 1 Temperature	310 - 320	°C
Barrel - Zone 2 Temperature	310 - 320	°C
Barrel - Zone 3 Temperature	315 - 320	°C
Barrel - Zone 4 Temperature	315 - 320	°C
Drying Temperature	130°C	°C
Drying Time	3-4 hours	hrs

PROCESSING PARAMETERS : see above typical injection molding conditions.

DRYING : is not essential when material is delivered in sealed bags with moisture content below 0.2 %.

BARRELS, SCREWS, MOULDS : use wear resisting steel or alloy such as bimetallic cylinders, nitrided screws.

USE OF REGRIND : the properties of the component should be checked in order to ascertain the maximum acceptable level of regrind.

SAFETY : please refer to Material Safety Datasheet.

CRLab 1331671 LR4111

(1) Typical values for natural color unless specified otherwise. Do not constitute a specification. Significant variations are possible for colors

Starflam, Staramide and Starpylen are registered trademarks of EUROSTAR Engineering Plastics

All information, recommendation or advice given by Eurostar Engineering Plastics Company, or any of its subsidiaries, affiliates or authorized representatives, is given in good faith. Eurostar Engineering Plastics makes no warranty or guarantee, express or implied about the information provided. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of Eurostar Engineering Plastics, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. Eurostar Engineering Plastics cannot be held responsible respectively liable for any loss incurred through the use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of Eurostar Engineering Plastics or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.